



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁷:

B27N 3/18, 3/08, 3/24

A1

(11) International Publication Number:

WO 00/44540

(43) International Publication Date:

3 August 2000 (03.08.00)

(21) International Application Number: PCT/SE00/00186

(22) International Filing Date: 31 January 2000 (31.01.00)

(30) Priority Data:

9900331-1

1 February 1999 (01.02.99)

SE

(71) Applicant (for all designated States except US): VALMET
FIBERTECH AB [SE/SE]; S-851 94 Sundsvall (SE).

(72) Inventors; and


(75) Inventors/Applicants (for US only): ERIKSSON, N., Lennart
[SE/SE]; Klackvägen 37, S-858 53 Sundsvall (SE). LUND-
GREN, Göran [SE/SE]; Metkroksvägen 2, S-865 91 Alnö
(SE).(74) Agents: JOHANSSON WEBJÖRN, Ingmar et al.; L.A. Groth
& Co.KB, P.O. Box 6107, S-102 32 Stockholm (SE).

(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published

With international search report.

(54) Title: METHOD AND ARRANGEMENT FOR THE CONTINUOUS MANUFACTURE OF PROFILED LIGNOCELLULOSE-CONTAINING BOARD OR STRIP-LIKE PRODUCTS



(57) Abstract

In a method and an arrangement for continuously producing profiled, lignocellulose-containing board or strip-like products the fibre material is disintegrated into particle and/or fibre form, which are then dried, glue-coated and formed into a fibre mat (3). This is pressed into a board or strip-like product (4) while injecting steam. Prior to pressing, the fibre mat (3) is given a surface profile, which is maintained during the steam injection process, whereupon the surface of the board or strip-like product is compressed with this profile.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

METHOD AND ARRANGEMENT FOR THE CONTINUOUS MANUFACTURE OF PROFILED LIGNOCELLULOSE-CONTAINING BOARD OR STRIP-LIKE PRODUCTS

5 The present invention relates to a method of continuously producing profiled lignocellulose-containing board or strip-like products according to the preamble of claim 1, and to an arrangement for carrying out the method in accordance with the preamble of claim 7.

10 A common way of producing, e.g., profiled structural elements such as skirting boards, cornices, window linings, architraving or furniture components is to plane or mill the desired profile either from solid wood or from fibreboard, preferably MDF (Medium Density Fibreboard). The unsuitability of using this technique to mill such products from medium density fibreboard is obvious. Firstly, it would involve a production chain and transport chain consisting of many expensive intermediate steps and operations and would mean that the profiled product would
15 have different densities in cross-section and therewith absorb different amounts of paint or varnish at discrete locations. The milling operation would also result in high material losses. For instance, more than 50% of the starting material can be lost when milling products to pronounced profile depths.

20 A standard example of this production chain may be as follows: Dried and glue-coated fibres are produced in the MDF plant and shaped into mats which are pressed into boards which are then edge-trimmed and ground. Losses are experienced in the form of edge trim and dust from the grinding operations. The next link in the production chain consists in the transportation of board to the production
25 unit for the profiled products. In the third link, the medium density fibreboards are sawn into strips which form the starting blanks for the profiled products, these starting blanks being milled and ground as well as lacquered with layers of paint or varnish or are coated with some type of film for priming or decoration purposes.

30 The object of the present invention is to avoid the drawbacks associated with the aforesaid production process in an economical fashion and, instead, to provide a continuous process up to the finished profiled product with as little mate-

rial loss as possible. This object is achieved in accordance with the invention having the characteristic features set forth in the following Claims.

The invention will now be described in more detail with reference to the accompanying drawing, which illustrates schematically in longitudinal section an inventive plant with four separate cross-sections shown in larger scale.

The illustrated plant is based on the plant illustrated in SE 502 272, which describes a continuous steam injection process. Disintegrated, dried and glue-coated lignocellulosic fibre material is delivered to a forming station 1 and there formed into a fibre mat 3 which is fed into a steam injection press 2. The fibre mat is pressed in the press into a board product 4 which is hardened, or cured, to an extent at which the board is solid and has a given mechanical strength. The surfaces are further densified in a surface densifying unit 5. This process results in board that has a dense outer surface.

According to the invention, the plant is designed for the production of profiled board or strip products in one and the same two-step process. To this end, a milling or cutting roll 6 is arranged between the forming station 1 and the steam injection press 2. The cutting roll 6 functions to impart a profiled surface structure to the lignocellulosic, glue-coated starting material in the form of the fibre mat 3 that has a density of between 20 and 200 kg/m³. To this end, the diameter of the cutting roll 6 varies across its width. The profile imparted to the cross-section of the mat will coincide essentially with the cross-section of the finished product. The profiled mat 3, which may be precompressed, is transported continuously into the steam injection press 2. This press includes a profiled steam roll 7 that has the same profile as the cutting roll 6. The mat 3 is compressed here and hardened to form a board or strip 4 that has the intended cross-section, by injecting saturated or superheated steam into the mat. The surface layers are further compressed in a second step, by allowing the board or the strip 4 to pass through the surface densifying unit 5 that includes one or more hot, compression roll-pairs 8 that have the same geometry as the steam roll 7 but a smaller cross-sectional area so as to obtain the desired surface compression. The surface temperature of the roll pairs 8 may lie between 100 and 350°C, preferably between 150 and 250°C.

The drawing shows the cross-section 9 of the formed fibre mat 3 prior to profiling the mat. The cross-section 10 downstream of the cutting roll 6 illustrates the profile of the upper surface. Downstream of the steam injection press 2, the board 4 pressed therein will have the cross-section 11, and the surface sheet in the cross-section 12 downstream of the surface densifying unit 5 will have a higher density but the same profile.

The underside of the board can be profiled with the same technique. In this respect, a cutting roll 6 is also arranged on the other side of the fibre mat 3 and the lower rolls 7 and 8 in the steam injection press 2 and the surface densifying unit 5 are provided with the same surface profile as the lower cutting roll across the respective widths thereof.

It may be of interest in certain applications to provide certain parts of the profile with a greater density, e.g. on exposed tops. This is made possible by allowing the profile on the rolls 7 and 8 to deviate from the profile on the cutting roll 6 at these points.

In one alternative embodiment, the board or the strip produced in the first step, i.e. in the steam injection press, can be divided into several narrower strips in a continuous process, these narrower strips then being passed through one or more hot roll pairs 8 in the surface densifying unit 5. Separation of the board or strip into a plurality of strips may be effected by sawing, for instance.

The invention enables the production of profiled lignocellulose-containing products in the form of boards and strips of uniform density throughout the whole of their cross-section and with dense surfaces that absorb equal amounts of paint over the entire product in a rapid and continuous process. Furthermore, this is achieved in the absence of losses in starting material, apart from the small losses that occur when sawing the board or strip.

CLAIMS


1. A method of continuously manufacturing profiled lignocellulose-containing board or strip-like products, wherein lignocellulosic fibre material is disintegrated to a particle and/or fibre form and the particles or fibres then dried, glue-coated and formed into a fibre mat which is pressed in a steam injection press to produce board or a strip-like product (4), **characterized** in that prior to being pressed the fibre mat (3) is given a surface profile which is maintained during the steam injection process, whereupon the surface of the board or strip-like product is compressed.
2. A method according to claim 1, **characterized** in that the fibre mat is formed with a bulk density of between 20 and 200 kg/m³.
3. A method according to claim 1 or 2, **characterized** in that the fibre mat is precompressed.
4. A method according to any one of claims 1 - 3, **characterized** in that the steam injected board or strip-like product is divided continuously into narrower strips prior to said surface compression.
5. A method according to any one of claims 1 - 4, **characterized** in that the board or strip-like product is given a varying density across said surface.
6. A method according to any one of claims 1 - 5, **characterized** in that a surface profile is formed on both the top and bottom sides of the product.
7. Arrangement for applying the method according to any one of claims 1 - 6 and comprising a forming station (1), an injection press (2) for pressing a fibre mat (3) arriving from the forming station (1) into a board or strip-like product (4), and a surface densifying unit (5) for further treating said product, **characterized** in that at least one milling or cutting roll (6) is provided between the forming station (1)

and the steam injection press (2) for providing the fibre mat with a surface profile; and in that the steam injection press (2) and the surface densifying unit (5) are each provided with at least one roll (7 and 8 respectively) that are profiled across their width.

5

8. Arrangement according to claim 7, **characterized** in that the steam roll (7) in the steam injection press (2) has the same profile as the milling or cutting roll (6) whereas the press roll (8) in the surface densifying unit has a profile whose diameter is greater than that of the profile on the steam roll (7) at certain extreme

10 points.



INTERNATIONAL SEARCH REPORT

International application No.

PCY/SE 00/00186

A. CLASSIFICATION OF SUBJECT MATTER

IPC7: B27N 3/18, B27N 3/08, B27N 3/24

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7: B27N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5179986 A (LAUREN J. BEUVING ET AL), 19 January 1993 (19.01.93), column 1, line 12 - line 22, abstract --	1-8
A	SE 502272 C2 (SUNDS DEFIBRATOR INDUSTRIES AB), 25 Sept 1995 (25.09.95), page 4, line 28 - line 38, abstract -- -----	1-8

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

3 May 2000

Date of mailing of the international search report

17-05-2000

Name and mailing address of the ISA/

Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Ulrika Nilsson/MP
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

02/12/99

International application No.

PCT/SE 00/00186

Patent document cited in search report			Publication date	Patent family member(s)	Publication date
US	5179986	A	19/01/93	US 5129435 A	14/07/92
SE	502272	C2	25/09/95	AT 182831 T	15/08/99
				AU 674473 B	19/12/96
				AU 688758 B	19/03/98
				AU 1673395 A	15/08/95
				AU 6390494 A	11/10/94
				CA 2179503 A	03/08/95
				CN 1137769 A	11/12/96
				CZ 282782 B	15/10/97
				CZ 284373 B	11/11/98
				CZ 9502491 A	13/03/96
				CZ 9601972 A	16/10/96
				DE 69415000 D,T	22/04/99
				DE 69511242 D	00/00/00
				EP 0690895 A,B	10/01/96
				EP 0741635 A,B	13/11/96
				ES 2134438 T	01/10/99
				FI 962977 A	26/07/96
				HU 77664 A	28/07/98
				HU 9601933 D	00/00/00
				JP 8508060 T	27/08/96
				JP 9508328 T	26/08/97
				NZ 279569 A	24/11/97
				PL 176748 B	30/07/99
				PL 310802 A	08/01/96
				PL 315629 A	25/11/96
				SE 9400266 A	29/07/95
				SI 9520019 A	28/02/97
				SK 89396 A	04/12/96
				SK 119095 A	04/06/97
				SK 279254 B	05/08/98
				US 5749992 A	12/05/98
				WO 9520473 A	03/08/95